



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B01J 23/34, C01B 21/26, 21/22	A1	(11) International Publication Number: WO 98/25698 (43) International Publication Date: 18 June 1998 (18.06.98)
(21) International Application Number: PCT/US97/20830 (22) International Filing Date: 12 November 1997 (12.11.97) (30) Priority Data: 96123343/04 10 December 1996 (10.12.96) RU (71) Applicant (for all designated States except US): SOLUTIA INC. [US/US]; 10300 Olive Boulevard, St. Louis, MO 63141 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): MOKRINSKII, Vladimir Vasilievich [RU/RU]; Apartment 94, 13 Russian Street, Novosibirsk, 630058 (RU). SLAVINSKAYA, Elena Markovna [RU/RU]; Apartment 94, 14 Ekvatornaya Street, Novosibirsk, 630058 (RU). NOSKOV, Alexander Stepanovich [RU/RU]; Apartment 14, 9 Tsvetnoy Road, Novosibirsk, 630058 (RU). ZOLOTARSKII, Ilya Aleksandrovich [RU/RU]; Apartment 2, 9 Detskii Road, Novosibirsk, 630058 (RU). (74) Agent: GOODMAN, Kenneth, D.; Arnold, White & Durkee, P.O. Box 4433, Houston, TX 77210-4433 (US).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: AMMONIA OXIDATION CATALYST COMPRISING ALUMINIUM OXIDE, BISMUTH OXIDE AND MANGANESE OXIDE (57) Abstract <p>Catalyst claimed to be used to produce nitrous oxide by ammonia oxidation with oxygen. The invention aims at providing catalysts exhibiting a high activity, when oxygen content in reaction mixture is close or lower the stoichiometry one, and high selectivity towards nitrous oxide and low selectivity towards nitrogen oxides. The catalyst composition is as follows, mass.‰: manganese oxide (referred to MnO₂) 5.0–35.0; bismuth oxide 4.5–30.0; aluminium oxide 35.0–90.5; specific surface area is 5–80 m²/g.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

AMMONIA OXIDATION CATALYST COMPRISING ALUMINIUM OXIDE, BISMUTH OXIDE AND MANGANESE OXIDE

The present invention describes catalysts to be used for nitrous oxide production by ammonia oxidation with molecular oxygen in chemical industry.

5 Along with a high activity, understood as conversion at a definite residence time, catalysts for ammonia oxidation to produce nitrous oxide should also meet the following demands:

- they should provide a high selectivity towards nitrous oxide and a low selectivity towards nitrogen oxide in the whole temperature range of ammonia oxidation;
- 10 • they should perform well under conditions, when reaction mixture contains oxygen in stoichiometry amount or below the stoichiometry amount.

As a rule, the known catalysts do not comply with all above demands.

Thus a bulk manganese-bismuth catalyst [1] containing 5% Bi_2O_3 and 95% MnO_2 has a low activity. At a temperature of 200°C , when the selectivity towards nitrous oxide is
15 maximum, and equals 88.5% at an inlet ammonia concentration of 10.8 vol.% in the oxygen excess, a complete ammonia conversion occurs at a residence time of 5 s. Meanwhile the selectivity towards NO and NO_2 is 0.9%. As the process temperature increases to 300°C , the yields of nitrous oxide and $\text{NO}+\text{NO}_2$ are 79 and 3.1% respectively. As ammonia concentration decreases to 3.02 vol.%, the selectivity towards nitrous oxide falls to 65%.

20 Therefore, beside a low activity in ammonia oxidation by the oxygen excess, the catalyst shows a high selectivity towards nitrogen oxides.

Another catalyst for ammonia oxidation consists of the oxides of iron, bismuth and manganese in the following ratio: 79.45% Fe_2O_3 , 11.53% Bi_2O_3 , 7.21% MnO_2 [2]. The maximum yield of nitrous oxide in the said catalyst is 82%, and it is attained under the
25 following conditions: temperature - 350°C ; inlet concentrations: ammonia - 10 vol.%, oxygen - 90 vol%. However, at this temperature the selectivity towards nitrogen oxide is 6%. At 300°C the selectivity towards nitrous oxide and nitrogen oxide is 79% and 1.5% respectively. Therefore, the catalyst does not meet all demands in concern, because it has a low selectivity towards nitrous oxide at a high selectivity towards nitrogen oxide.

- 2 -

Catalyst with a composition of 5% MnO_2 , 5% Bi_2O_3 , 90% Fe_2O_3 [3] is most close in performance and properties to the catalyst claimed in the present invention. It shows the following results. The maximum nitrous oxide yield is 87%, when reaction mixture containing 10% of ammonia in air (thus in oxygen excess, concentration 18.9 vol.%). If
5 reaction mixture contains 1 ammonia part, 5 air parts, and 5 nitrogen parts, and so it is close to stoichiometry (9.1 vol.% ammonia and 9.55 vol.% oxygen), then the yield of nitrous oxide is 81%. At 275-300°C the residence time for complete conversion is 3.6 s. Therefore, the catalyst has a low activity and not high enough selectivity towards nitrous oxide under conditions, when reaction mixture contains ammonia and oxygen in amounts close to
10 stoichiometry.

The present invention aims at providing catalysts that are highly active under conditions, when reaction mixture contains oxygen in amount close or below the stoichiometry one, showing a high selectivity towards nitrous oxide, and a low selectivity towards nitrogen oxide.

15 For the purpose the claimed catalysts for the nitrous oxide production by ammonia oxidation have the following composition (mass.%):

5.0-35.0 - manganese oxide (referred to MnO_2)

4.5-30.0 - bismuth oxide (Bi_2O_3)

90.5-35.0 - aluminum oxide (Al_2O_3).

20 The catalysts of the said composition are prepared by impregnating alumina with a solution of Mn and Bi nitrates, or by mixing the powders of Mn and Bi oxides with the powder of aluminum hydroxide to be then molded, or depositing the said components on an inert support. At the final stage the catalysts are dried, and calcined at 375-550°C. Thus obtained catalysts show a high activity, when the oxygen content in the reaction mixture is
25 close or lower the stoichiometry one, and exhibit a high selectivity towards nitrous oxide, and a low selectivity towards nitrogen oxide.

At a temperature of 350°C, and at a residence time of 0.7 sec, ammonia/oxygen ratio being 1.44, and ammonia concentration being 7.3 vol.%, ammonia conversion on the said catalysts is 82-99.2%. The selectivity towards nitrous and nitrogen oxides is 82-84.6 and 2.1-

- 3 -

2.7% respectively. After water and ammonia separation the final product contains 79.6-81.7% of nitrous oxide, 4.1-5.25% of nitrogen oxide, and 0.82-0.84% of oxygen.

At a temperature of 300°C, and at a residence time of 1.6 sec, ammonia/oxygen ratio being 1.44, and ammonia concentration being 7.3 vol.%, ammonia conversion on the said catalysts is 82.5-99.0%. The selectivity towards nitrous and nitrogen oxides is 83-86 and 0.3-0.35% respectively. After water and ammonia separation the final product contains 82.2-84.9% of nitrous oxide, 0.6-0.69% of nitrogen oxide, and 0.75-0.77% of oxygen.

The high activity and selectivity of the claimed catalysts in ammonia oxidation to nitrous oxide is provided by its components at the said percent ratios.

Catalyst specific surface area also has a positive effect. The tests show that at a stable high activity the catalyst shows the highest selectivity, when its specific surface area ranges within 5-80 m²/g.

Example 1. Catalyst with a composition of 13%MnO₂/11%Bi₂O₃/76%Al₂O₃ is prepared as follows. 100 g of alumina granules are impregnated by incipient wetness with a solution of Mn and Bi nitrates, are dried in air and then in a drying chamber at 130°C for 2-4 h. Thus obtained product is once again impregnated with a solution of Mn and Bi nitrates, dried in air and in the drying chamber at 130°C for 4 hours. Then the granules were calcined in a furnace at 375-550°C for 2-4 h. Thus obtained catalyst is tested under reaction conditions similar to those described in [3], reaction mixture composition being 9%NH₃ and 9%O₂. At 350°C and at a residence time of 0.7 s ammonia conversion is 99.2%. Selectivity towards nitrous oxide and nitrogen oxide is 87 and 2.8% respectively. At 300°C at the same gas composition and at a contact time of 1.6 s ammonia conversion is 99.4%. Selectivity towards nitrous oxide and nitrogen oxide is 88.6 and 0.30% respectively. Ssp is 10 m²/g.

Example 2. Catalyst prepared as in example 1 is tested at ammonia to oxygen ratio equal to 1.44 and ammonia concentration equal to 7.3 vol.% in the reaction mixture.

At 350°C and at a residence time of 0.7 s ammonia conversion is 82%. Selectivity towards nitrous oxide and nitrogen oxide is 84.6 and 2.7% respectively. In the final product nitrous oxide to oxygen ratio is 97.4, nitrous oxide to nitrogen oxide ratio being 15.6. After

- 4 -

ammonia and water separation the final product contains 82% of nitrous oxide, 5% of nitrogen oxide, and 0.84% of oxygen.

At 300°C at the same gas composition and at a contact time of 1.6 s ammonia conversion is 82.5%. Selectivity towards nitrous oxide and nitrogen oxide is 86 and 0.35% respectively. In the final product nitrous oxide ratio to oxygen is 110, while nitrous oxide to nitrogen oxide ratio is 121. The final product (after ammonia and water separation) contains 85.2% of nitrous oxide, 0.7% of nitrogen oxide, and 0.78% of oxygen.

Example 3. Catalyst with a composition of 5%MnO₂/5%Bi₂O₃/Fe₂O₃ is prepared as described in [3] and tested under the following conditions: reaction mixture composition - 0.75%NH₃, 1.5%O₂; residence time - 0.072 s, temperature - 350-300°C. At 350°C ammonia conversion is 73%. Selectivity towards nitrous oxide and nitrogen oxide is 76.9 and 3.9% respectively. At 300°C ammonia conversion is 35%. Selectivity towards nitrous oxide and nitrogen oxide is 68 and 1.4% respectively. Ssp is 4 m²/g.

Example 4. Catalyst with a composition of 15%MnO₂/15%Bi₂O₃/70%Al₂O₃ is prepared as in example 1 and tested as in example 2. At 300°C ammonia conversion is 38%. Selectivity towards nitrous oxide and nitrogen oxide is 79 and 1.4% respectively. Ssp is 11 m²/g.

Example 5. Catalyst with a composition of 13%MnO₂/11%Bi₂O₃/76%Al₂O₃ is prepared as in example 1 and tested as in example 2. At 350°C ammonia conversion is 76%. Selectivity towards nitrous oxide and nitrogen oxide is 76% and 3.8% respectively. At 300°C ammonia conversion is 39%. Selectivity towards nitrous oxide and nitrogen oxide is 83 and 1.3% respectively.

Example 6. Catalyst with a composition of 15%MnO₂/7.5%Bi₂O₃/77.5%Al₂O₃ is prepared as in example 1 and tested as in example 2. At 350°C ammonia conversion is 93.2%. Selectivity towards nitrous oxide and nitrogen oxide is 78.7% and 3.9% respectively. At 300°C ammonia conversion is 58.7%. Selectivity towards nitrous oxide and nitrogen oxide is 80 and 1.2% respectively. Ssp is 11 m²/g.

Example 7. Catalyst with a composition of 10%MnO₂/5%Bi₂O₃/85%Al₂O₃ is prepared as in example 1 and tested as in example 2. At 350°C ammonia conversion is 92.5%.

- 5 -

Selectivity towards nitrous oxide and nitrogen oxide is 80% and 3.7% respectively. At 300°C ammonia conversion is 62.4%. Selectivity towards nitrous oxide and nitrogen oxide is 77 and 1.3% respectively. Ssp is 11 m²/g.

Example 8. Catalyst with a composition of 16%MnO₂/16%Bi₂O₃/68%Al₂O₃ is
5 prepared as in example 1 and tested as in example 2. At 350°C ammonia conversion is 73%. Selectivity towards nitrous oxide and nitrogen oxide is 78.8% and 3.9% respectively. At 300°C ammonia conversion is 37%. Selectivity towards nitrous oxide and nitrogen oxide is 37 and 1.4% respectively. Ssp is 39 m²/g.

Example 9. Catalyst with a composition of 5%MnO₂/4.5%Bi₂O₃/90.5%Al₂O₃ is
10 prepared as follows. 100 g of alumina granules are impregnated by a solution of Mn and Bi nitrates, dried in air and in the drying chamber at 120-130°C for 4 h. The obtained product was calcined in the furnace in air at 375-550°C for 2-4 h. Thus obtained catalyst was tested as in example 2. At 350°C ammonia conversion is 79%. Selectivity towards nitrous oxide and nitrogen oxide is 76% and 3.6% respectively. At 300°C ammonia conversion is 40%.
15 Selectivity towards nitrous oxide and nitrogen oxide is 80 and 1.3% respectively. Ssp is 5 m²/g.

Example 10. Catalyst with a composition of 35%MnO₂/30%Bi₂O₃/35%Al₂O₃
prepared mixing a mass containing 52 g of Mn oxide and Bi oxide powders and 35 g of aluminum hydroxide powder with 25 cm³ of water to obtain a moldable paste. Then the paste
20 was molded as cylinder granules 3 mm in diameter, dried at room temperature for 10 h, dried in the chamber at 120°C for 2 h, and calcined in the furnace at 375-550°C for 2-4 h. Thus obtained catalyst was tested as in example 2. At 350°C ammonia conversion is 77%. Selectivity towards nitrous oxide and nitrogen oxide is 78% and 3.1% respectively. At 300°C ammonia conversion is 39%. Selectivity towards nitrous oxide and nitrogen oxide is 74 and
25 1.1% respectively. Ssp is 80 m²/g.

References:

1. V.F. Postnikov, L.L. Kuz'min and N.K. Tsal'm, - J.Chem.Ind., 22, 1348 (1937)
2. Zawadzki, Discussions Faraday Soc., 1950, N8, p.140
3. Schlecht, L., and von Nagel, A., Ger. Patent 503200 (1930)

- 6 -

Table 1

example	content, mass. %		conversion, %	S _{N2O} , %	S _{NO} , %	T°C
	MnO ₂	Bi ₂ O ₃				
1	13	11	99.2	87	2.8	350
			99.4	88.6	0.35	300
2	13	11	82	84.6	2.7	350
			82.5	86	0.35	300
3	5	5	73	76.9	3.9	350
			35	68	1.4	300
4	15	15	38	79	1.4	300
5	13	11	76	76	3.8	350
			39	83	1.3	300
6	15	7.5	93.2	78.7	3.9	350
			58.7	80	1.2	300
7	10	5	92.5	80	3.7	350
			62.4	77	1.3	300
8	16	16	73	78.8	3.9	350
			37	74.7	1.4	300
9	5	4.5	79	76	3.6	350
			40	80	1.3	300
10	35	30	77	78	3.1	350
			39	74	1.1	300

- 7 -

CLAIMS:

1. A catalyst for production of nitrous oxide, comprising MnO_2 , Bi_2O_3 , and Al_2O_3 .

5 2. The catalyst of claim 1, where the catalyst comprises:

about 5.0-35.0 % MnO_2 ;

about 4.5-30.0% Bi_2O_3 ; and

about 35.0-90.5% Al_2O_3 .

10 3. The catalyst of claim 1, where the specific surface area of the catalyst is about 5-80 m^2/g .

4. The catalyst of claim 1, where the specific surface area of the catalyst is about 10-40 m^2/g .

15 5. The catalyst of claim 1, where the catalyst consists essentially of:

about 5.0-35.0 % MnO_2 ;

about 4.5-30.0% Bi_2O_3 ; and

about 35.0-90.5% Al_2O_3 .

20 6. The catalyst of claim 1, where the catalyst comprises:

about 13 % MnO_2 ;

about 11 % Bi_2O_3 ; and

about 76 % Al_2O_3 .

25 7. The catalyst of claim 1, where the catalyst comprises:

about 15 % MnO_2 ;

about 15 % Bi_2O_3 ; and

about 70 % Al_2O_3 .

- 8 -

8. The catalyst of claim 1, where the catalyst comprises:
about 15 % MnO_2 ;
about 7.5 % Bi_2O_3 ; and
about 77.5 % Al_2O_3 .

5

9. The catalyst of claim 1, where the catalyst comprises:
about 10 % MnO_2 ;
about 5 % Bi_2O_3 ; and
about 85 % Al_2O_3 .

10

10. The catalyst of claim 1, where the catalyst comprises:
about 16 % MnO_2 ;
about 16 % Bi_2O_3 ; and
about 68 % Al_2O_3 .

15

11. The catalyst of claim 1, where the catalyst comprises:
about 5 % MnO_2 ;
about 4.5 % Bi_2O_3 ; and
about 90.5 % Al_2O_3 .

20

12. The catalyst of claim 1, where the catalyst comprises:
about 35 % MnO_2 ;
about 30 % Bi_2O_3 ; and
about 35 % Al_2O_3 .

25

INTERNATIONAL SEARCH REPORT

Inte. onal Application No

PCT/US 97/20830

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 B01J23/34 C01B21/26 C01B21/22

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B01J C01B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WERTHER J, HENGER B: "Ermittlung optimaler Betriebseinstellungen für technische Wirbelschichtreaktoren" CHEM. -ING. -TECH, vol. 52, no. 2, 1980, pages 106-113, XP002058296 See page 110, point 4.1 ----	1-12
X	MASSIMILLA L, JOHNSTONE HF: "Reaction Kinetics in fluidized beds" CHEMICAL ENGINEERING SCIENCE, vol. 16, 1961, pages 115-112, XP002058297 See pages 107-108, "Catalyst" ----- -/--	1-12

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

11 March 1998

Date of mailing of the international search report

24/04/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Dack, S

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 97/20830

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>SHEN CY, JOHNSTONE HF: "Gas-solid Contact in Fluidized Beds" A.I.C.H.E., vol. 1, no. 3, March 1955, pages 349-354, XP002058298 See page 350, "Catalyst"</p> <p style="text-align: center;">---</p>	1-12
X	<p>US 5 212 137 A (SURESH DEV D ET AL) 18 May 1993 see column 4, line 61 - column 5, line 9; examples 1-13</p> <p style="text-align: center;">---</p>	1
X	<p>US 4 419 274 A (SIN YOON K ET AL) 6 December 1983 see examples 1-4,6</p> <p style="text-align: center;">-----</p>	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 97/20830

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5212137 A	18-05-93	US 5093299 A	03-03-92
		AT 109769 T	15-08-94
		BG 60911 B	28-06-96
		CN 1053197 A, B	24-07-91
		DE 69011495 D	15-09-94
		DE 69011495 T	08-12-94
		EP 0437056 A	17-07-91
		ES 2057448 T	16-10-94
		JP 7047271 A	21-02-95
		MX 172776 B	11-01-94
		RU 2038146 C	27-06-95
		US 5175334 A	29-12-92
<hr/>			
US 4419274 A	06-12-83	DE 3126675 A	05-08-82
		JP 1341628 C	14-10-86
		JP 57102234 A	25-06-82
		JP 61007330 B	05-03-86
<hr/>			